

TECHNICAL DATA SHEET

ROCKCOTE ARMOUR FLEX

Last Updated January 2017

Description ROCKCOTE Armour Flex is a high build, high performance protective coating. It is a water resistant and highly flexible acrylic membrane that can be applied by nap roller, texture roller, brush or spray gun. ROCKCOTE Armour Flex is ideally suited to applications that require a superior level of protection, such as high rise buildings, commercial buildings and areas of high coastal exposure

Features

- 10 year warranty*
- Water based
- Excellent flexibility
- Vapour permeable
- Easy to maintain

Benefits

- Excellent colour retention
- Very high water resistance
- Long term exterior protection
- Mould resistant
- Scuff resistant
- Easy to use
- Easy to maintain
- Very high resistance to cracking
- Will bridge existing cracks of up to 1mm

Uses

- Will provide a standard low profile paint finish or medium build stipple finish over substrates such as brick, block, ROCKCOTE renders and textures, concrete, cement sheeting and A.A.C. panels/blocks
- Designed to be used where a superior level of crack resistance and a superior level of protection against water ingress is required
- Provides excellent added durability and ensures a low maintenance coating when combined within a ROCKCOTE System
- Can be used interior and exterior

Colours and Gloss Can be tinted to a wide range of colours. For exterior applications it is recommended that light-fastness of chosen colours be confirmed before ordering

Sheen Level Available in Matt and Low Sheen

Typical Data at 25°C and 50% Relative Humidity

Volume Solids	50%
Thinning	Up to 5% for cutting in & spraying and up to 5% for first coat when applying over acrylic texture and render
Coverage Rate	Coverage Rate: Low Profile: 3.0m ² /ltr p/coat Medium Stipple Profile: 2.0m ² /ltr p/coat Based on smooth substrate
Film Build	Dry film build: Low Profile: 160 µm p/coat Medium Profile: 200-250 µm p/coat Wet film build: Low Profile: 330 µm p/coat Medium Profile: 400-500 µm p/coat
Drying Time	6-8 hours
Touch Dry	2 hours
Dry to Recoat	6-8hrs
Elongation Rate	700% (ASTM D-412)
Crack Bridging	8.9 times DFT (AS4548.5/F Static Test)
Moisture Control	Excellent
Abrasion Resistance	Excellent
Usual No Coats	2
Packaging Sizes	15 Ltr & 4 Ltr pails
Clean Up	Water

Substrate Conditions

- Must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants and contain less than 15% moisture [WME]
- Do not apply if air and surface temperatures are below 5°C or above 35°C
- If applying over ROCKCOTE Q Render, application may proceed after 48hrs if properly cured

TECHNICAL DATA SHEET

ROCKCOTE ARMOUR FLEX

Last Updated January 2017

and contains less than 15% WME

- Fresh cementitious substrates such as site mix sand and cement render or concrete must be left for up to 28 days to sufficiently cure and contain no more than 15% WME prior to application
- Anti Efflorescent Primer must be used when coating cementitious substrates such as site mix sand and cement render
- Up to 5% water can be added to first coat, when applying over acrylic texture and render

Flooring Installation

N/A

Mixing

N/A

Application

- To ensure colour consistency, the same paint batch should be used on the finish coat. If this is not possible then multiple pails should be boxed together
- Be sure to keep a wet edge with this product and plan your work to suit the product and weather conditions. See ROCKCOTE's Technical Article on "Cutting In and avoiding picture framing"
- It is best practice to finish at an external or internal corner, or at a control line when work will continue the next day
- Keep sheltered from rain and moisture for 24-48 hrs after completion dependent on climatic conditions
- For a standard low profile paint finish, use a 20mm nap sheepskin roller sleeve (for airless spray use 0.021.. To 0.025 .. Tips)
- For a textured stipple effect use a fine or medium texture roller sleeve
- Applicator must check colour prior to application. ROCKCOTE will not accept liability once product has been applied

Safety Data

Refer to ROCKCOTE Armour Flex SDS

Precautions and Limitations

- Should not be applied in temperatures below 5°C or above 35°C
- Not suitable for areas of continual damp or areas submerged in water
- Not suitable for floors.

Transport and Storage

- Store in a cool dark place
- Keep pail sealed
- Do not stack over 3 high

Disposal

- Spilt Material must be absorbed with sand/sawdust and lifted for proper disposal
- Product must not be allowed to run into drains or open bodies of water
- Residual small amounts of leftover paint on brushes and rollers should be wiped on to an old newspaper and allowed to dry, rather than being washed down the sink. Dispose of in accordance with local council regulations
- Suitable for disposal through the RA Industries Reclaimer Portable Paint Wash Recycling System

Disclaimer

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.

* WHEN USED AS PART OF A FULL ROCKCOTE SYSTEM.