# **Technical Data Sheet**

# ROCKCOTE CLAY PLASTER DECOR

## Effective From 18 Sep, 2020

ROCKCOTE Clay Plaster Décor is a truly beautiful fine finishing clay plaster with built-in marble dust that glistens in the presence of ambient light. An earthen-look plaster with a smooth finish, ROCKCOTE Clay Plaster Décor adds textural warmth to the interior of any building - from a traditional straw bale home to the most elegant modern building.

#### Features

- Dry, clean and chopped wheat, straw, hemp hurd, rice husks, quartz chips, marble chips and shells can be added to create beautiful and unique effects.
- Can be used to achieve a range of specialist finishes and textures.
- Zero VOC.

#### Benefits

- Can add character to alfresco areas with natural toned feature walls or highlights.
- Allows surfaces to breathe, contributing to improved indoor air quality.
- Ability to create textural depth in a smooth, flat surface.
- Ideal for people conscious about their health and the health of their families.

#### Uses

- Suitable for interior use only.
- Finishing plaster for use over natural plasters or modern substrates.
- For added durability, apply ROCKCOTE Repel.

#### **Colours and Gloss**

• Soft white. Can be tinted to a wide range of colours using oxides.

#### Sheen Level

Coverage Rate	Approximately 4m2/15kg bag @2mm build
Application Method	Trowel
Dry Film Build	2 – 6mm
Wet Film Build	

#### Typical Data at 25°C and 50% Relative Humidity

Drying Time	24 to 48 hours
Touch Dry	
Curing Time	7 days
Usual No Coats	1 or 2 Coats
Clean Up	Water
Packaging Sizes	15Kgs
Abrasion Resistance	
Water Resistance	
Pot Life	

#### Substrate Conditions

Substrate must be installed as per manufacturer's specifications. Substrate must be clean and free of dust, dirt, oil, salt, mould or any other contamination. Any base coats should be fully cured. Substrates must not contain more than 15% moisture prior to the application of ROCKCOTE Clay Plaster Decor. For full details on application for each substrate, refer to the ROCKCOTE Natural Materials Systems Guide.

# **Technical Data Sheet**



ROCKCOTE CLAY PLASTER DECOR

**Effective From** 18 Sep, 2020

## Mixing

Add one 15kg bag of ROCKCOTE Clay Plaster Décor to 3 – 3.5 litres of clean water. Mix for a minimum of 3 minutes. Allow mixture to sit for 10 - 15 minutes and adjust consistency, if required, before use.

# Application

- ROCKCOTE Clay Plaster Décor can be applied by a traditional hawk and trowel, screeded, floated, trowelled, sponged, texture brushed and undulated to give many desired texture finishes.
- Clean and dry chopped wheat straw, hemp hurd, rice husks, quartz chips, marble chips, chopped wheat or rice straw can be added.

## **Precautions and Limitations**

- ROCKCOTE Clay Plaster Décor should not be applied in temperatures below 5°C or above 35°C.
- ROCKCOTE Clay Plaster Décor is not suitable for areas of continual damp or areas submerged in water.
- Not suitable for external application or wet areas such as shower recesses or splashbacks.
- ROCKCOTE does not recommend the use of any ROCKCOTE Natural Materials on floors.

**Transport and Storage** ROCKCOTE Clay Plaster Decor must be kept dry during transport and storage. Disposal

• Dispose of in accordance with local council regulations

#### Safety Data

**Refer ROCKCOTE Clay Plaster Décor SDS** 

#### Disclaimer

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.