

Technical Data Sheet

ROCKCOTE CLEARCOTE

Effective From 05 Jan, 2022

ROCKCOTE Clearcote is a clear, acrylic finish developed to provide added resistance against water ingress, mould/grime pick-up and retention over the complete range of ROCKCOTE finishes. ROCKCOTE Clearcote can be used as a top coat over ROCKCOTE Coloured Renders and specialist products to provide extra protection.

Features

- Water based
- Excellent flexibility
- Vapour permeable
- Easy to maintain

Benefits

- High water resistance
- Long term exterior protection
- Mould resistant
- Scuff resistant
- Easy to use
- High resistance to cracking

Uses

- Provides a highly water repellent and mould resistant surface when applied over ROCKCOTE texture coatings.
- Can be used as a top coat over ROCKCOTE Coloured Renders and specialist products to provide extra protection.
- Can be used interior and exterior.

Colours and Gloss

Dries to a clear semi gloss finish.

Sheen Level Semi gloss

Coverage Rate 20m²/ltr

Application Method Brush, Roller or Spray

Dry Film Build 12 microns

Wet Film Build 50-60 microns (parameters will change according to substrate suction).

Typical Data at 25°C and 50% Relative Humidity

Drying Time 4 hours

Touch Dry 2 hours

Dry to Recoat 4 hours

Usual No Coats 1

Clean Up Water

Packaging Sizes Trade 20L 15L 10L 4L 1L

Volume Solids

Thinning Do not thin

Elongation Rate

Crack Bridging

Abrasion Resistance Excellent

Moisture Control Excellent

Water Resistance Excellent

Pot Life

Technical Data Sheet

ROCKCOTE CLEARCOTE

Effective From	05 Jan, 2022
-----------------------	--------------

Substrate Conditions

- Must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.
- All substrates must be installed as per manufacturers' specifications prior to application.
- Do not apply if air and surface temperatures are below 5°C or above 35°C.

Application

- Should be applied evenly as possible by brush, roller or spray equipment, ensuring complete coverage whilst maintaining a wet edge.
- After application with a medium nap roller it is important to tip off the product to ensure an even appearance and drying.
- Care should be taken not to apply too much product on cut-in areas.
- An 80mm wide roller of medium nap pile should be used for cutting in.
- Allow a minimum of 4 hours between applications.
- Keep sheltered from rain and moisture for 12-24 hours after completion dependent on climatic conditions.
- See ROCKCOTE's Technical Article on "Cutting In and avoiding picture framing".

Precautions and Limitations

- Should not be applied in air and surface temperatures below 5°C or above 35°C.
- Should not be applied over glossy silicone based paints or sealants.

Transport and Storage

- Store in a cool dark place
- Keep pail sealed
- Do not stack over 3 high

Disposal

- Spilt Material must be absorbed with sand/sawdust and lifted for proper disposal
- Product must not be allowed to run into drains or open bodies of water
- Residual small amounts of leftover paint on brushes and rollers should be wiped on to an old newspaper and allowed to dry, rather than being washed down the sink. Dispose of in accordance with local council regulations
- Suitable for disposal through the RA Industries Reclaimer Portable Paint Wash Recycling System

Technical Data Sheet



ROCKCOTE CLEARCOTE

Effective From	05 Jan, 2022
-----------------------	--------------

Safety Data

Refer ROCKCOTE Clearcote SDS

Disclaimer

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.