

Technical Data Sheet

ROCKCOTE PEARLCOTE

Effective From 03 Apr, 2023

ROCKCOTE Pearlcode provides a seamless and natural solid rendered look, with the flexibility and performance required for all solid masonry substrates and modern lightweight walling systems. ROCKCOTE Pearlcode incorporates the unique beauty and natural sparkle of fine sand to provide an attractive and natural looking coloured render finish.

Features

- Water based
- Ease of use, no sponge finishing required
- Vapour permeable

Benefits

- Tough
- Flexible
- Water resistant
- Excellent adhesion
- Long term exterior protection
- Natural coloured render finish that does not require painting

Uses

- ROCKCOTE Pearlcode is suitable for application over properly prepared substrates such as brick, block, cement render, ROCKCOTE Render, concrete, cement sheeting, A.A.C. panels/blocks and plasterboard.
- Can be used interior and exterior.
- Can be over coated with ROCKCOTE Repel or Clearcode for added durability and low maintenance.

Colours and Gloss

- Available in light base only.

Sheen Level Semi-gloss

Coverage Rate 12-15m²/15ltr
Coverage rates may vary according to substrate and preparation.

Application Method Trowel

Dry Film Build 1mm

Wet Film Build

Typical Data at 25°C and 50% Relative Humidity

Drying Time 24 hours

Touch Dry 5 hours

Dry to Recoat 24 hours

Usual No Coats 1

Clean Up Water

Packaging Sizes Trade 20L ☐ 15L ☒ 10L ☐ 4L ☐ 1L ☐

Volume Solids

Thinning Up to 5%

Elongation Rate

Crack Bridging Bridge cracks up to 900µm per applied coat

Abrasion Resistance Excellent

Moisture Control

Water Resistance Excellent

Pot Life

Technical Data Sheet

ROCKCOTE PEARLCOTE

| | |
|-----------------------|--------------|
| Effective From | 03 Apr, 2023 |
|-----------------------|--------------|

Substrate Conditions

- ROCKCOTE PearlCote must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.
- Substrates must not contain more than 15% moisture (WME) prior to application.
- Do not apply if air and surface temperatures are below 5°C or above 35°C.
- If applying over ROCKCOTE Quick Render, application may proceed after 48 hours if properly cured.
- Fresh cementitious substrates such as site mix sand and cement render and concrete must be left for up to 28 days to sufficiently cure prior to application of ROCKCOTE PearlCote.
- ROCKCOTE Anti Efflorescent Primer should be used when applying over site mix render.

Application

- Check colour before use.
- Ensure same batch numbers are used on a single wall where possible.
- Mix to help reactivate and aerate contents.
- Apply evenly over the properly prepared substrate with a hawk and trowel.
- Ideally apply slightly thicker than the sand granules to achieve optimum results.
- Use circular motions to finish with a plastic float/trowel.
- Be sure to keep a wet edge with this product and plan your work to suit the product and weather conditions.
- If joining up to previous day's application, it is "good working practice" to start and finish on an external or internal corner.
- Keep sheltered from rain and moisture for 24 - 48 hours after completion dependent on climatic conditions.
- It is advisable to apply a primer that is tinted to the required finish colour before the application of ROCKCOTE PearlCote.

Precautions and Limitations

- Check colour before use.
- Ensure same batch numbers are used on a single wall where possible.
- Should not be applied in temperatures below 5°C or above 35°C.
- Not suitable for areas of continual damp or areas submerged in water.

Transport and Storage

- Store in a cool dark place
- Keep pail sealed
- Do not stack over 3 high

Disposal

- Dispose of in accordance with local council regulations

Technical Data Sheet

ROCKCOTE PEARLCOTE

| | |
|-----------------------|--------------|
| Effective From | 03 Apr, 2023 |
|-----------------------|--------------|

Safety Data

Refer to ROCKCOTE Pearlcote SDS

Disclaimer

Rockcote Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, Rockcote Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.