

Rockcote Polymer Render Off White

Active From:

03 Sep 2025

Rockcote Polymer Render Off White is a flexible acrylic based coating which is especially suitable for application over substrates where tolerance to movement and good adhesion must be considered. Rockcote Polymer Render Off White sponges to an attractive coarse finish and is ideal for being overcoated with Rockcote top coats.

Features

- Premixed and ready to apply.
- Flexible and highly crack resistant.
- Excellent adhesion qualities.
- Can be sponge finished.

Uses

- Suitable for application over properly prepared substrates such as brick, block, cement render, Rockcote render, concrete, fibre cement sheeting, AAC panels/blocks and plasterboard.
- Can be used for interior and exterior applications.
- Must be overcoated with Rockcote Coloured Render, texture or protective membrane paint.

Colours and Gloss

- Not designed as a coloured finish, but can be tinted to assist in coverage of subsequent coloured coatings.

Coverage Rate: 10m²/15L @ 1mm DFT

Coverage rates vary according to substrate, application technique, wastage factors and substrate preparation.

Application Method: Trowel or Spray

Dry Film Build: 1-2mm

Wet Film Build: Approx 1mm per coat

Typical Data at 25°C and 50% Relative Humidity

Drying Time: 24-48 hours

Touch Dry: 3 hours (when applied over a primed substrate)

Dry to Recoat: 24 hours (when applied over a primed substrate)

No of Coats: 1 or 2

Clean Up: Water

Packaging Sizes: 15L

Crack Bridging: Excellent

Substrate Conditions

- Must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants
- Substrates must not contain more than 15% WME prior to application
- Do not apply if air and substrate temperatures are below 5°C or above 35°C.
- If applying over Rockcote Quick Render, application may proceed after 48 hours if properly cured.
- Fresh cementitious substrates such as concrete and site mix render must be left for up to 28 days to sufficiently cure prior to application.
- Rockcote Anti Efflorescent Primer should be used when applying over site mix render.

Rockcote Polymer Render Off White

Active From:

03 Sep 2025

Application

- Mix thoroughly prior to application.
- Apply evenly over the properly prepared substrate.
- Must be applied to a minimum of 2mm dry film build over fibre cement sheet.
- Apply slightly thicker than the aggregate to achieve the desired result.
- Using circular motions, finish with a plastic float/trowel and if required, finish with a soft damp sponge.
- Be sure to keep a wet edge with this product and plan your work to suit the product and weather conditions.
- Best applied in two coats to achieve a uniform finish.
- Keep sheltered from rain & moisture for 24-48 hours after completion dependent on climatic conditions.

Precautions and Limitations

- Not suitable for areas of continual damp or areas submerged in water.
- Must be overcoated with a Rockcote Coloured Render, texture or paint within 14 days of application..

Transport and Storage

- Store in a cool dark place.
- Keep pail sealed.
- Do not stack over 3 high.

Disposal

- Dispose of in accordance with local council regulations

Safety Data

Refer Rockcote Polymer Render SDS.

Disclaimer

Rockcote Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, Rockcote Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.