

Technical Data Sheet

ROCKCOTE QUICK RENDER SUPER FINE

Effective From	15 Sep, 2020
-----------------------	--------------

ROCKCOTE Quick Render Super Fine is a pre-blended cement render. ROCKCOTE Quick Render Super Fine uses finer grade sands and fillers than standard pre-blended renders and can be used where an extremely fine and smoother textured render finish is required. Aesthetically, Super Fine is the finest of our Quick Render range and is designed to look like a smooth site mix render.

Features

- Easy to use
- Excellent adhesion to properly prepared substrates

Benefits

- Tough
- Long term exterior protection
- Water repellent
- Can be painted after 48 hours (site mix sand and cement must be cured for 28 days prior to coating)
- Saves time and money
- Can reduce scaffold costs, when used instead of site mix sand and cement render.

Uses

- ROCKCOTE Quick Render Super Fine is suitable for application over properly prepared substrates such as brick, block, concrete, AAC blocks, panels, tilt up and off form concrete.
- Can be used interior and exterior.
- ROCKCOTE Quick Render Super Fine is ideal to use as a base coat for ROCKCOTE acrylic Coloured Renders, roll on textures and membrane paints and coatings.
- ROCKCOTE Quick Render Super Fine should be overcoated within 28 days of application.

Colours and Gloss

Sheen Level

Coverage Rate

Approximately 2m²/20kg @ 4mm build

Application Method

Trowel or Spray

Dry Film Build

4-8mm

Wet Film Build

Optimum results are normally achieved by applying at 4 - 8mm thick per coat. ROCKCOTE Quick Render Super Fine should not be applied in a single coat greater than 10mm thick. If total thickness of coating system is to exceed 10mm, and is to be less than 30mm, use ROCKCOTE PM100 High Build as a base coat prior to the application of ROCKCOTE Quick Render Super Fine. For coating systems greater than 30mm, contact ROCKCOTE Technical Department.

Typical Data at 25°C and 50% Relative Humidity

Drying Time 8 hours

Touch Dry

Curing Time 48 hours

Dries in approximately 8 hours under normal drying conditions. (Dry times vary with changes in temperature and humidity and residual moisture in the substrate). Once initial dry set has occurred, rewet 2 to 3 times a day with clean water for 2 days. This is especially important during hot and/or windy weather.

Usual No Coats

Suitable for 1 coat application depending on substrate and method of application.

Clean Up

Clean with water immediately after use if render has not cured. Remove any unwanted material or spatter from surfaces with water as soon as possible and

Technical Data Sheet

ROCKCOTE QUICK RENDER SUPER FINE

Effective From	15 Sep, 2020
-----------------------	--------------

preferably before dry. Recently dried render may be more easily removed with warm water and detergent.

Packaging Sizes	20Kgs
Abrasion Resistance	Excellent
Water Resistance	
Pot Life	

Substrate Conditions

- ROCKCOTE Quick Render Super Fine must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.
- Do not apply ROCKCOTE Quick Render Super Fine if air and surface temperatures are below 5°C or above 35°C.
- All brick and masonry substrates must be wet down prior to the application of ROCKCOTE Quick Render Super Fine. Application should proceed when the wet "shine" has disappeared.
- For dense, smooth and difficult substrates ROCKCOTE Keycote must be applied prior to ROCKCOTE Quick Render Super Fine application to provide optimum adhesion.
- When applying over AAC, such as Hebel panels or blocks, seal first with one coat of ROCKCOTE Acrybond mixed with an equal part of water to control suction and improve adhesion.

Application

- For traditional hawk and trowel hand application, mix 20 kg of ROCKCOTE Quick Render Super Fine to 3 - 3.5L of gauging liquid (water) for a minimum of 3 minutes, let stand for a further 3 minutes and re-mix and adjust to desired consistency.
- If the ROCKCOTE Quick Render Super Fine is to be applied less than 4mm thick per coat dry film build, 10% ROCKCOTE Acrybond must be added to the water.
- ROCKCOTE Quick Render Super Fine should not be applied in a single coat greater than 10mm.
- ROCKCOTE Quick Render Super Fine can be sprayed on with a suitable machine such as Mortatec Worker or Mortarman.
- ROCKCOTE Quick Render Super Fine can be shaved flat, floated and sponged or just shaved if applying a ROCKCOTE Coloured Render system.
- All windows and doors should be masked up to avoid damage and for ease of cleaning.
- Keep the finished ROCKCOTE Quick Render Super Fine sheltered from rain & moisture for 24 hours after completion dependent on climatic conditions.

Precautions and Limitations

- ROCKCOTE Quick Render Super Fine should not be applied in temperatures below 5°C or above 35°C.
- ROCKCOTE Quick Render Super Fine is not suitable for application over fibre cement sheeting, EPS, XPS and swimming pools.
- Can be applied up to 10mm per coat.

Technical Data Sheet

ROCKCOTE QUICK RENDER SUPER FINE

Effective From	15 Sep, 2020
-----------------------	--------------

Transport and Storage

- ROCKCOTE Quick Render Super Fine must be kept dry during transportation and storage.
- When working with ROCKCOTE Quick Render Super Fine, observe the usual precautions for handling cement based products.
- Avoid inhalation of the powder, prolonged skin contact and particularly eye contact.
- If contact occurs, flush thoroughly with clean water.
- Wear protective clothing to minimise skin contact and wear goggles where spatter is likely.
- Where spills occur, sweep up dry material or soak up liquid spillage with sand/sawdust and remove to suitable disposal.

Disposal

- Dispose of in accordance with local council regulations

Safety Data

Refer ROCKCOTE Quick Render Super Fine SDS.

Disclaimer

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.