

Technical Data Sheet

ROCKCOTE SANTINI

Effective From 14 Jan, 2021

ROCKCOTE Santini will provide a medium to heavy "bagged" finish when applied with a sponge or sheepskin mitt. ROCKCOTE Santini can be tinted to any colour and does not need to be overcoated, unlike a traditional bagged finish that requires two coats of paint. ROCKCOTE Santini is also 100% acrylic and provides excellent flexibility and durability.

Features

- Water based
- Ease of use
- Inexpensive way to achieve a rendered finish
- Vapour permeable

Benefits

- Tough
- Flexible
- Water resistant
- Excellent adhesion
- Long term exterior protection
- Can minimise surface imperfections
- Tinted in the same way as paint, ensuring colour consistency

Uses

- ROCKCOTE Santini is suitable for application over properly prepared substrates such as brick, block, cement render, ROCKCOTE render, concrete, cement sheeting, AAC panels/blocks, and plasterboard.
- Can be used interior and exterior.
- Primarily for decoration and protection of surfaces but will also camouflage minor imperfection within a substrate.
- Can be over coated with ROCKCOTE Armour for added durability and lower maintenance.

Colours and Gloss

- Low Sheen when over coated with ROCKCOTE Armour/Flex.
- Available in white base only.

Sheen Level Matt

Coverage Rate 8-15m²/15ltr

Coverage rates may vary according to the condition of the substrate, desired finish or method of application. ROCKCOTE Santini is usually applied at the rate of approximately 8–15 square metres per 15 litre drum. Care must be taken to avoid excessive build-up in corners and at reveals.

Application Method Trowel, High Build Texture Roller or Sheepskin Mitt

Dry Film Build Approximately 1.5mm

Wet Film Build Up to 3mm

Typical Data at 25°C and 50% Relative Humidity

Drying Time 24 hours

Touch Dry 4 hours

Dry to Recoat 24 hours

Usual No Coats 1

Clean Up Water

Packaging Sizes Trade 20L 15L 10L 4L 1L

Technical Data Sheet

ROCKCOTE SANTINI

Effective From	14 Jan, 2021
-----------------------	--------------

Volume Solids

Thinning Up to 5%

Elongation Rate

Crack Bridging Bridge cracks up to 900µm per applied coat.

Abrasion Resistance Excellent

Moisture Control

Water Resistance Excellent

Substrate Conditions

- It is advisable to apply a primer that has been tinted to the required finish colour to ensure colour consistency.
- ROCKCOTE Santini must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.
- Substrates must not contain more than 15% moisture (WME) prior to the application of ROCKCOTE Santini.
- Do not apply ROCKCOTE Santini if air and surface temperatures are below 5°C or above 35°C.
- If applying over ROCKCOTE Quick Render, application of ROCKCOTE Santini may proceed after 48 hours if properly cured.

Application

- The application of ROCKCOTE Santini is a specialised procedure and should only be carried out by a skilled and experienced applicator in accordance with ROCKCOTE's specifications.
- If using multiple pails of ROCKCOTE Santini contents must be boxed together to ensure colour consistency.
- Be sure to keep a wet edge with this product and plan your work to suit the product and weather conditions. See ROCKCOTE's Technical Article on Cutting In and avoiding "Picture Framing".
- If joining up to previous day's application, it is "good working practice" to start and finish on an external or internal corner.
- Keep the finished ROCKCOTE Santini sheltered from rain and moisture for 24-48 hours after completion dependent on climatic conditions.
- Can be applied with a high build texture roller, trowel or by sheepskin mitt to achieve desired finish.

Precautions and Limitations

- ROCKCOTE Santini should not be applied in temperatures below 5°C or above 35°C.
- ROCKCOTE Santini is not suitable for areas of continual damp or areas submerged in water.

Transport and Storage

- Store in a cool dark place.
- Keep pail sealed.
- Do not stack over 3 high.

Disposal

- Dispose of in accordance with local council regulations

Technical Data Sheet

ROCKCOTE SANTINI

Effective From	14 Jan, 2021
-----------------------	--------------

Safety Data

Refer to ROCKCOTE Santini SDS.

Disclaimer

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.