



Durable Beauty.

MicroStone is easy to use and offers excellent adhesion qualities. Durable and easy to maintain when sealed, it provides a unique appearance that embodies the true essence of luxury. Suitable for properly primed and prepared substrates such as brick, block, cement render, Rockcote render, concrete, cement sheeting, and plasterboard. MicroStone can also be over-coated with Rockcote MicroFinish Sealers for added durability and lower maintenance on walls, floors, and wet area applications.

Application System

| System | Wet Pendulum Slip Rating | Dry Pendulum Slip Rating |
|--|--------------------------|--------------------------|
| Vertical Surfaces - 2 x coats of MicroFinish IV | | |
| MicroPrime - 1st coat MicroStone - 1st coat MicroStone - 2nd coat Lightly sanded with sandpaper - PS11A P240 MicroFinish III Penetrating Sealer - 1 coat MicroFinish IV Hydrophobic Sealer (MS 20) - 1st coat MicroFinish IV Hydrophobic Sealer (MS 20) - 2nd coat (after 1 hour) | P2 | D1 |
| Wet Area Horizontal Surfaces - 2 x coats of MicroFinish IV (with anti slip additive) | | |
| MicroPrime - 1st coat MicroStone - 1st coat MicroStone - 2nd coat Lightly sanded with sandpaper - PS11A P240 MicroFinish III Penetrating Sealer - 1 coat MicroFinish IV Hydrophobic Sealer (MS 20) +2.4% ptx 50 - 1st coat MicroFinish IV Hydrophobic Sealer (MS 20) +2.4% ptx 50 (Anti Slip additive) - 2nd coat (after 1 hour) | P4 | D1 |
| Vertical Surfaces - 2 x coats of MicroFinish II | | |
| MicroPrime - 1st coat MicroStone - 1st coat MicroStone - 2nd coat Lightly sanded with sandpaper - PS11A P240 MicroFinish III Penetrating Sealer - 1 coat MicroFinish II Polyurathane - 1st coat MicroFinish II Polyurathane - 2nd coat (after 3 hours) | P2 | D1 |
| Wet Area Horizontal Surfaces - 2 x coats of Microfinish II (with anti slip additive) | | |
| MicroPrime - 1st coat MicroStone - 1st coat MicroStone - 2nd coat Lightly sanded with sandpaper - PS11A P240 MicroFinish III Penetrating Sealer - 1 coat MicroFinish II Polyurathane - 1st coat MicroFinish II Polyurathane +2.4% ptx 50 (Anti Slip Additive) - 2nd coat (after 3 hours) | P5 | D1 |